


MAXIMO 920

Zinc Oxide



Product
specification



MAXIMO 920

Zinc Oxide



RUBBER

Zinc oxide is an essential compound in the rubber vulcanization (curing) process. Although its largest application is in tires, it is a critical ingredient in all rubber products, including gaskets, hoses, electrical insulation, shoe soles, conveyor belts, bellows, medical products and many other general rubber products.



Packaging:

Bag: 25 kg, 50 lb,
Big Bag: 1000 kg

Typical Chemical Analysis

Purity	99.0 %	Minimum
Zinc (Zn)	79.5 %	Minimum
Lead (Pb)	0.07 %	Maximum
Iron (Fe)	0.06 %	Maximum
Cadmium (Cd)	0.02 %	Maximum
Loss on Ignition	0.50 %	Maximum
PH	6 - 8	
Fineness: Through 325 Mesh Screen	99.90 %	Minimum



CORPORATE OFFICE

Serafín Peña 938 Sur, Centro
Monterrey, N.L., México, Zip Code 64000
Phone: +52(81)8342 6861, 8345 4078
sales@gpromax.com

METALLURGICAL PLANT

Pedro Galindo 101, Lomas del Roble,
San Nicolás de los Garza
N.L., México, Zip Code 66450
Phone: +52(81)8376 5024, 8376 5783
purchase_metalurgica@gpromax.com
sales_metalurgica@gpromax.com

SDR

13209 Highway 96
Millport, Alabama, USA, Zip Code 35576
Phone: 1(205)662 8801
Fax: 1(205)662 8802
aleyva@steeldust.com
fmontemayor@steeldust.com

DISTRIBUTION CENTER

Boulevard Benito Juárez 23
Bodega No.9, San Mateo Cuautepec
Tultitlán, Estado de México, Zip Code 54948
Phone: +52(55)5705 0197, 5705 0203
sales@gpromax.com

TURKMEX

Çoraklar Mahallesi,
5012 Sokak, No.43, 35800
Aliağa OSB (İzmir-Çanakkale E87 Karayolu
67.km), Aliağa / İzmir / TÜRKİYE
Phone: +90(850)622 6030, 232 621 5300
infotmx@turkmex.com.tr

GSDK

23, Yulchonsandan 2-ro,
Haeryong-myeon, Suncheon-si,
Jeonnam, South Korea
Zip Code 58035
Phone: +82(61)740 2700
info@gsdkorea.com

TOLL FREE CALLS
FROM WITHIN THE US:
1 855 268 4664